



## TECHNICAL DATA SHEET

### R-ZHFR-3006H

### Halogen Free Low Smoke Flame Retardant Compound (HFFR/ZHFR/LSZH)

#### Product Description:

Product Description: R-ZHFR-3006 H is a thermoplastic RoHS Compliance, Halogen Free, Flame Retardant, UV resistance Low Smoke, moisture resistance (HFFR/LSZH) cable compound. It combines low smoke density with very good flame retardancy. The compound is based on Non-toxic and Non corrosive elements and it has excellent mechanical & electrical properties.

#### Specifications:

The cables manufactured with R-ZHFR-3006 H is meets the following specifications;

\* IEC 332-1 / IEC 332-2, \* BS 7655: Section 6.1, \* IS 17048, \* VDE 0207 PART 24 HM2 & HM4, \* EN 50363-7:2005, \* 3m<sup>3</sup> smoke density chamber test to IEC 61034-2, BS EN 50290-2-27 for type HM2 and HD 604 for type HM4 & GR TEC 89010:2021.

#### Applications :

R-ZHFR-3006 H is intended for extrusion & molding products with high hardness. It can also be used in areas to low smoke /low corrosive and low toxic combustion products.

#### Technical Parameters :

Sr. No.	Parameter	Test Method	Unit	Typical Value
01.	Density (Max)	ASTM D 792	gm/cc	1.56
02.	Melt Flow Index (160°C/21.6 kg)	ASTM D 1238	gm/10 minute	5
03.	Tensile Strength at Break	ASTM D 638	Mpa (N/mm <sup>2</sup> )	10
04.	Elongation at Break	ASTM D 638	%	150
05.	Tensile Strength after ageing for 7 days at 100°C	ASTM D 638	%	+10
06.	Elongation after ageing for 7 days at 100°C	ASTM D 638	%	- 13
07.	Hardness (Min)	ASTM D 2240	Shore-D	57
08.	Limiting Oxygen Index (LOI)	ASTM D 2863	%	30
09.	Temperature Index	ASTM D 2863	°C	>270
10.	Smoke Density	ASTM D 2843	%	<10
11.	HCl & HBr gas generation	IEC 60754-1	%	<0.2
12.	Volume Resistivity	ASTM D 257	Ohm-cm	1 x 10 <sup>14</sup>
13.	pH	IEC 60754-2	pH	> 5
14.	Conductivity	IEC 60754-2	Micro s/mm	< 7
15.	Ozone resistance test	IS 10810-13	-	Passed
16.	Water immersion test at 70°C @7days	IS 17048 (5.13)	-	Passed
	Variation in tensile strength		%	-22
	Variation in elongation at break		%	-20

\*Mechanical properties are tested on 1 mm extruded tape.



## R-ZHFR-3006H



### Colorability:

R-ZHFR-3006 H is available in natural color, but it is colorable compound with EVA/PE base color master batch.

### Shipment:

R-ZHFR-3006 H is supplied in the form of free-flowing granules in 25 kg moisture proof poly bags or 860 kg in octagon.

### Processing Guidelines:

- R-ZHFR-3006 H can be processed using low C/R screw instead of regular PE extruder. The actual temperature profile for extrusion will depend on the machine characteristics but the following can be taken as a guideline; Temperature Profile: 135-145-155-160-160-165°C.
- To obtain smooth and glossy cable surface, it is recommended for pre-drying at 70°C for 2 to 4 hours.

### Storage and Handling:

- The material should be stored to prevent a direct exposure to sunlight and/or heat.
- The storage area should also be dry and preferably don't exceed 50°C. RTL would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance.
- It is advisable to process goods within 1 year from the date of manufacturing.

